

<b>Subject:</b>	<b>2007 Edition of EN ISO 2409</b>		
<b>Proposal of the coating section of QUALISURFAL:</b>	The 2007 version of the standard mentions the use of a 50 mm adhesive tape rather than 25 mm.		
<b>QUALICOAT resolution:</b>	<b>Meeting held on 21 November 2007</b> <i>(ratified on 26 June 2008)</i>		
<b>Date of application:</b>	<b>July 2008</b>		
<b>Amendments to the Specifications:</b>	<b>Section 2.4 Adhesion</b> <b>Appendix A9 - List of relevant standards</b>		
<p><b>2.4 Adhesion</b></p> <p><b>EN ISO 2409</b></p> <p>The adhesive tape must be conform to the standard (strength adhesion = (10 +/- 1) N per 50 mm width). The spacing of the cutters must be 1 mm for coating thicknesses of up to 60 µm, 2 mm for thicknesses between 60 µm and 120 µm, and 3 mm for thicker coatings.</p> <p><b>REQUIREMENTS:</b></p> <p>The result must be 0.</p>			
<b>Appendix A9 - List of relevant standards</b>			
<b>EN ISO 2409</b>	<b>2007</b>	Paints and varnishes -- Cross-cut test	<b>Adhesion</b> 2.4, 6.3.4